

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B68G 1/00, A47G 9/00, D01F 2/02, D04H 1/00, 1/42, 1/02	A1	(11) International Publication Number: WO 99/16705 (43) International Publication Date: 8 April 1999 (08.04.99)
(21) International Application Number: PCT/GB98/02619 (22) International Filing Date: 1 September 1998 (01.09.98) (30) Priority Data: 9720436.6 26 September 1997 (26.09.97) GB (71) Applicant (for all designated States except US): FIBRETECH LIMITED [GB/GB]; Brook Mill, Hollins Road, Oldham OL8 4JY (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): BLACK, Robert, Paul [GB/GB]; New Pale Lodge, Manley, Cheshire WA6 9EZ (GB). (74) Agent: W.P. THOMPSON & CO.; Coopers Building, Church Street, Liverpool L1 3AB (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: FILLING COMPRISING A POLYESTER FIBRE (57) Abstract <p>The present invention relates to a filling comprising a polyester fibre. More particularly it relates to an improved polyester fibre containing filling for use where thermal properties and/or breathability are important, such as in the soft furnishings industry, where it may be used as a filling for bedding, for example duvets, pillows, mattress protectors and sleeping bags or in the clothing industry where it may be used as a filling for coats, anoraks, and the like, particularly ski and winter wear. Polyester fibre, usually polyethyleneterephthalate, is an inexpensive alternative to down or feathers. However it lacks breathability. In an attempt to improve the characteristics of a filling comprising polyester fibre, the polyester fibre has been blended with natural materials such as, for example, cotton, silk, down and feathers. The improvement comprises mixing the polyester with a cellulosic fibre obtained by an organic solvent spinning process to produce a non-woven blend with improved thermal and/or breathability properties. The non-woven may be in the form of fibreballs, a wadding, a padding, a stuffing or a filling material.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

DESCRIPTIONFILLING COMPRISING A POLYESTER FIBRE

The present invention relates to a filling comprising a polyester fibre. More particularly it relates to an improved polyester fibre containing filling for use where thermal properties and/or breathability are important, such as in the soft furnishings industry, where it may be used as a filling for bedding, for example duvets, pillows, mattress protectors and sleeping bags or in the clothing industry where it may be used as a filling for coats, anoraks, and the like, particularly ski and winter wear.

Polyester fibre, usually polyethyleneterephthalate, is an inexpensive alternative to down or feathers. However it lacks breathability. In an attempt to improve the characteristics of a filling comprising polyester fibre, the polyester fibre has been blended with natural materials such as, for example, cotton, silk, down and feather.

Considerable effort has been made in the industry to provide an improved synthetic filling and in particular one with improved breathability.

It is an aim of the present invention to provide a synthetic fibrefill with improved breathability but which retains at least some of the desirable properties of polyester fibrefill.

It has unexpectedly been found that cellulosic fibres obtained by an organic solvent spinning process, and in particular one in which the organic solvent is N-methyl morpholine oxide (NMMO) e.g. lyocell, when blended (in

- 2 -

contrast to woven) with a polyester filling fibre such as, for example, polyethyleneterephthalate gives rise to a product with improved characteristics including improved breathability compared to a polyester filling fibre alone. The finding was unexpected given that lyocell fibres are traditionally flat and would not have been expected to be a good filling fibre. Lyocell is a cellulosic fibre made by direct dissolution of wood pulp in an organic solvent and has to date been used primarily in the development of technical textiles, namely woven fabrics comprising interlaced warp and weft threads.

It is another aim of the present invention to provide a synthetic fibrefill with improved thermal performance.

It has unexpectedly been found that cellulosic fibre e.g. lyocell, when blended with a polyester filling fibre, such as, for example, polyethyleneterephthalate gives rise to a product with improved thermal characteristic compared to the component fibres alone.

According to the present invention there is provided a non-woven blend comprising or consisting of a polyester filling fibre and a cellulosic fibre obtained by an organic spinning process.

Preferably the cellulosic fibre is lyocell.

Preferably the polyester filling fibre is polyethyleneterephthalate fibre.

Preferably the blend comprises, by weight, no more than 80%, more preferably still 60%, of the cellulosic fibre, for example, lyocell.

More preferably the cellulosic fibre, for example, lyocell is present in an amount of from 10 - 60% by weight and ranges therebetween, more

preferably still 20- 60% and more preferably still from 25- 60% of the blend.

Preferably the polyester filling fibre comprises mono fibres which are crimped or conjugate fibres. By conjugate fibres is meant fibres comprising two different fibre-forming polymeric units arranged side by side so that on heat treatment the fibre becomes spirally crimped.

Preferably the cellulosic or lyocell fibre is a saw-toothed crimp fibre.

More preferably the cellulosic or lyocell fibres and polyester filling fibres are formed into a fibre ball. To form a fibre ball it is preferred to use a lyocell cellulosic fibre blended with a conjugate polyester preferably of polyethyleneterephthalate.

Alternatively a lyocell cellulosic fibre and either a conjugate polyester or a regular saw tooth crimp polyester fibre are blended, carded and layered into a wadding. For the avoidance of doubt a wadding is neither a woven product nor a fabric.

Preferably the wadding is more than 3 mm thick and more preferably more than 5 mm thick. It is a loose open material in contrast to compressed materials such as for example felts.

According to a further aspect of the present invention there is provided a bedding article comprising as a filling a non-woven blend of the invention.

According to a further aspect of the present invention there is provided an article of clothing comprising as a filling a non-woven blend of the invention.

The bedding article may be, for example, a duvet, pillow, quilt,

sleeping bag, cushion or other similar article.

The clothing article may be, for example, a jacket, coat, or anorak.

The non-woven blend has characteristics which make it more desirable than a polyester filling, for example, polyethyleneterephthalate alone:

- 1) it has a more down like feel;
- 2) weight for weight it is warmer than polyethyleneterephthalate; and
- 3) It is breathable, i.e. moisture absorbent;

Fibreballs of the non-woven blend also show improved breathability and thermal properties.

The blending of fibres, and the production of fibre balls are well known processes to the man skilled in the art and are not therefore described herein.

The invention will be further described, by way of example only, with reference to the tabulated test data shown in tables 1 and 2 below:

Table 1 shows the products under test; and

Tables 2 and 3 show the properties of the products under test.

It should be noted with reference to table 1 that pure lyocell has a fill weight of 49.3 gm/m²/tog, which is similar to the figure of 49 gm/m²/tog for pure polyester. The blend however gives a figure of 39 gm/m²/tog ie a synergistic and non obvious effect is achieved with a mixture.

TABLE 1

	Duvet Weight	U.K. Tog Test	Fill wgt gm/m ² /tog
Cellulosic/ Polyester Carded Blend	2060g	13.5	37
Goose down	1790g	13.5	18
Hollow Polyester fibre Carded	2488g	13.5	49

TABLE 2

	THERMOREGULATORY MODEL OF MAN (MANNIKIN) EFFECTIVE IN USE DATE	Thermal % Difference Insulation From (High best) Cellulosic	Effective % Difference Water Vapour From Resistance Cellulosic (low best)	Water % Difference Vapour From permeability Cellulosic (high best)	Ratio of Thermal % Difference Insulation From to weight Cellulosic (high best)	Thermal Physiological % Difference Comfort (temp. °C) (low best)
		THIS IS WARMTH RATING	THIS IS THE RESISTANCE TO WATER VAPOUR INVASION	THIS IS THE BREATHABILITY MOISTURE TRANSPORT PROPERTIES	WARMTH TO WEIGHT RATIO	MINIMUM TEMPERATURE BEFORE DISTURBED SLEEP
Cellulosic/Polyester Carded Blend	7.8		841	0.56	379	5.5°C
Goose down	7.3	-6.4%	845	0.52	490	7.1°C
Hollow polyester fibre	7.21	-7.6%	840	0.51	290	7.40°C

TABLE 3

	THERMOREGULATORY MODEL OF SKIN			Buffering Capacity Moisture Transport & Take-up properties	% Difference from Cellulosic
	Water Vapour Take-up (gm/m ²) (high best)	% Difference From Cellulosic			
Cellulosic/Polyester Carded Blend	42.0			5.0	
Goose down	42.8	+ 1.9%		4.1	- 18%
Hollow polyester fibre	26.5	-36.9%		4.1	- 18%
	ABILITY TO REMOVE WATER VAPOUR QTY			ABILITY TO TRANSPORT MOISTURE AWAY FROM BODY FROM SWEAT PULSE	
	RATE OF MOISTURE ABSORBANCE				

- 7 -

It will be noted from test results shown in tables 2 and 3 that the non-woven blend of the invention is significantly better than pure polyester (the current synthetic filling of choice) when it comes to its thermal insulation properties, its water vapour permeability index, its ratio of thermal insulation to weight, its thermal physiological comfort, its water vapour take up and its buffering capacity moisture transport and uptake properties and only insignificantly worse in its effective water vapour resistance. In other words, the non-woven blend confers a higher degree of thermal insulation and possesses better moisture transport properties under stationary conditions combined with better moisture absorption than a pure polyester material.

CLAIMS

1. A non-woven blend comprising or consisting of a polyester filling fibre and a cellulosic fibre obtained by an organic spinning process.
2. A non-woven blend as claimed in claim 1 wherein the cellulosic fibre is lyocell.
3. A non-woven blend as claimed in claim 1 or 2 wherein the polyester filling fibre is polyethyleneterephthalate fibre.
4. A non-woven blend as claimed in any of the preceding claims comprising, by weight, no more than 80% of the cellulosic fibre.
5. A non-woven blend as claimed in any of the preceding claims wherein the cellulosic fibre is present in an amount, by weight, of from 10-60% of the blend.
6. A non-woven blend as claimed in any of the preceding claims wherein the cellulosic fibre is present in an amount, by weight, of from 20-60% of the blend.
7. A non-woven blend as claimed in any of the preceding claims wherein the cellulosic fibre is present in an amount, by weight, of from 25-60% of the blend.
8. A non-woven blend as claimed in any of the preceding claims wherein the polyester filling fibre comprises monofibres which are crimped or conjugate fibres.
9. A non-woven blend as claimed in any of the preceding claims

- 9 -

wherein the polyester filling fibre comprises conjugate fibre.

10. A non-woven blend as claimed in any of the preceding claims wherein the cellulosic fibre is a saw-toothed crimp fibre.

11. Fibreballs comprising a non-woven blend as claimed in any of the preceding claims.

12. A wadding comprising a carded and layered non-woven blend as claimed in any of claims 1 to 10.

13. A padding, stuffing or filling material comprising a non-woven blend as claimed in any of claims 1 to 10.

14. A bedding article comprising a non-woven blend as claimed in any of claims 1 to 10, fibreballs as claimed in claim 11, a wadding as claimed in claim 12 or a padding, stuffing or filling material as claimed in claim 13.

15. A bedding article as claimed in claim 14 selected from the group consisting of a duvet, a pillow, a mattress, a mattress protector, a sleeping bag, a topper, a quilt, an enhancer, a comforter and a bed.

16. An article of clothing comprising a non-woven blend as claimed in any of claims 1 to 10, fibreballs as claimed in claim 11, a wadding as claimed in claim 12 or a padding, stuffing or filling material as claimed in claim 13.

17. An article of clothing as claimed in claim 16 selected from the group consisting of a coat, a jacket, an anorak, and ski or winter wear.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/02619

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B68G1/00 A47G9/00 D01F2/02 D04H1/00 D04H1/42
D04H1/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B68G A47G A47C D01F C08J D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 474 300 A (HURK R A VAN DEN) 11 March 1992 see the whole document ---	1-17
A	WO 96 09546 A (UNIPATH LTD) 28 March 1996 see example see page 8, line 19 - line 22 ---	1,4-7, 12-17
P,A	PATENT ABSTRACTS OF JAPAN vol. 098, no. 008, 30 June 1998 & JP 10 072771 A (ASAHI CHEM IND CO LTD), 17 March 1998 see abstract --- -/--	1-17

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

23 November 1998

Date of mailing of the international search report

04/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Barathe, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/02619

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication where appropriate, of the relevant passages	Relevant to claim No.
A	WO 93 06806 A (LAKISS SMITH ROSEMARIE) 15 April 1993 see page 3, line 5 - line 6 see page 3, line 24 - line 28 ----	1-17
A	GB 1 486 639 A (FREUDENBERG C) 21 September 1977 see examples ----	1-17
A	US 5 311 389 A (HOWEY JON A) 10 May 1994 see tables 5,6 -----	1-17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/02619

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0474300 A	11-03-1992	NL 9001951 A DE 69101231 D DE 69101231 T	01-04-1992 31-03-1994 01-06-1994
WO 9609546 A	28-03-1900	AU 3651395 A CA 2199823 A EP 0782707 A JP 10505909 T	09-04-1996 28-03-1996 09-07-1997 09-06-1998
WO 9306806 A	15-04-1993	AU 663735 B	19-10-1995
GB 1486639 A	21-09-1900	DE 2364382 B AU 7610074 A FR 2255415 A JP 50096637 A NL 7416553 A	06-03-1975 10-06-1976 18-07-1975 31-07-1975 24-06-1975
US 5311389 A	10-05-1994	US 5060105 A CA 2080419 A EP 0538971 A JP 7073634 A CA 2021511 A EP 0452536 A JP 4222976 A JP 7056106 B	22-10-1991 16-04-1993 28-04-1993 17-03-1995 17-10-1991 23-10-1991 12-08-1992 14-06-1995